



Yongtek Co., LTD

Tel: +886-3-316-0666/ Fax: +886-3-316-0655/ Email: sales@yongtek.com

12F, No.86-2, Yiwen 1st street, Taoyuan Dist, Taoyuan City 33045 Taiwan

Reflector Technical Data

Model Name: E6D8

Item	Unit	Direction	320 –E6D8	Test Method
Thickness	um		370	JIS C2151
Tensile Strength	MPa	MD	70	JIS C2151
		TD	50	JIS C2151
Elongation at Break	%	MD	70	JIS C2151
		TD	50	JIS C2151
Heat Shrinkage (90c × 30min)		MD	0.2	JIS C2151
		TD	0.0	JIS C2151
Gloss (60deg)	%	-	30	JIS Z8741
Surface Roughness (SRa)	nm	-	1800	JISB 0601-2001
Relative Reflectance	%	-	104	Hitachi U3310 (560nm)