

## **Test Report**

Report No. : T2014-08774

SEWON PRECISION & IND. CO., LTD. Company:

HA. Y.J. & KOO. M. H. Representative:

154-36, Gimhae-daero 916beon-gil, Hallim-myeon, Gimhae-si, Gyeongsangnam-do Address:

Polymethylmethacrylate Diffuser Plate[Model Name: PMMA Diffuser Plate DME] 1. Product Name:

- Type and Model:

Reference Data for the Quality Management 2. Use of Report:

2014.09.19. 3. Date of Receipt:

4. Date of Test: 2014. 09. 22. - 2014. 09. 25.

KS C IEC 60695-2-12 5. Testing Method:

Refer to the attachment(2 page) 6. Test Results:

Tested by: Seo, WonTae

从戏剧

Approved by: Chae, Heebong

- 1. This report is based on the test and analysis performed with the sample(s) submitted by the client. Therefore, the report does not quarantee the quality of entire products.
- 2. This report should not be used for advertising, lawsuit, etc. without any official permission of KTC. It is only used for the purpose of the quality test.
- 3. The copy of this report is invalid for use.

2014. 09. 25.



President


Korea Testing Certification

www.ktc.re.kr / 435-862 22, Heungan-daero 27beon-gil, Gunpo-si, Gyeonggi-do TEL: +82-31-428-7418, FAX: +82-31-455-7235

서식P510-07 (Rev.2)

Page:

1 of 2









## **Test Result**

Report No.: T2014-08774

Test Item	Test Method and Standard		Result
Glow Wire	If flames or glowing of the test specimen extinguish within 30 seconds after removal of the glow-wire. (Test temperatures : 650 $^{\circ}$ C)	GWFI 650/2.0	Pass
	When the specified layer of wrapping tissue is used there shall be no ignition of the wrapping tissue		Pass

## Remarks:

1. The test has been conducted with sample(s), test specifications and test methods submitted by the client.

서식P510-06 (Rev.2)

Page: 2 of 2



